
## TEST REPORT\_LAIKEMAN PVC FLOORONG



#### **TEST REPORT**

National Center of supervision&inspection on Sporting Goods

No: GT2103585

No: GT901299

No: GT1901300

	5 12 12 12 12 12 12 12 12 12 12 12 12 12		共2页第1页	
样品名称	PVC运动地胶	规格型号	lm×im	
		商标	<b>莱珂曼</b>	
委托单位	維县莱珂曼塑胶地板有限公司	样品等级		
委托单位 地址	河北省雄安新区雄县雄州路546号	送样人	李文杉	
受检单位	維县莱珂曼塑胶地板有限公司	检验类别	委托检验	
生产单位	<b>维县莱珂曼塑胶地板有限公司</b>	样品数量	1 m'	
样品描述	样品未见异常	生产日期/批号	2021. 8. 1	
检验日期	2021/8/11 至 2021/8/31	到样日期	2021/8/10	
判定依据	企业技术要求			
判定依据	企业技术要求 全項			
检验项目检验结论	全领	签发日期: 2021年9	施檢測专用報) 月26世出資	
检验项目	全领	THE THE PARTY OF T		

### No: GT2103585

Sample name: PVC sport flooring

**Inspected unit:** Xiongxian LAIKEMAN Plastic

Floor Co., LTD

Manufacturer: Xiongxian LAIKEMAN Plastic

Floor Co., LTD

Sample quantity: 1m<sup>2</sup>

**Specification Model:** 1mx1m

Trademark: LAIKEMAN

**Production date/batch number: 2021.8.1** 

**Inspection date:** 2021/8/11-2021/8/31

Sample description: No abnormality was

found in the sample

**Test basis:** GB/T2257.4-2017 GB/T14833-2020

GB/T20239-2015 GB/T20096-2006

字号	GT2103585	检验项目	单位	技术要求	检验结果	2页第2单项判定
	外观质量			色泽均匀,无明显色差,无 裂痕、分层等缺陷。	1	符合
2	邵氏硬度(邵A)		度	55~90	60	符合
3	拉伸强度		MPa	≥2. 0	2. 5	符合
4	拉断伸长率		%	≥90	99	符合
5	阻燃性		級		l I	符合
6	球反弹率		%	≥90	93	符合
7	高温试验(100℃, 24h)			试验后无融化、无明显色差	<b>J</b>	符合
8	低温试验 (~40°C, 24h)			试验后无龟裂、无明显色差	<b>,</b>	符合
9	滑动摩擦系数			0.4~1.5	1.2	符合
10	耐老化性 能 (168h)	老化后的外观质量		老化后色泽均匀,无明显色 差,无裂痕、分层等缺陷	1	符合
		老化后的拉伸强度	MPa	≥2.0	2. 2	符合
		老化后的拉斯伸长率	%	≥80	91	符合
	备注: "√	表示符合技术要求。	×*表示不行	所有技术要求。 <sup>*</sup> ── <sup>*</sup> 表示未怕!	<b>或不作判定。以</b> F	**************************************

Judgment basis: enterprise technical

requirements

Inspection items: All items

**Conclusion:** The sample meets the technical

requirements of the enterprise

Date of Issue: September 26, 2021

## No: GT2103585 Item of Inspection

**Appearance quality:** uniform color, no obvious color difference, no cracks, stratification and other defects.

Shaw Hardness (Shao A): 60 degrees (55 ~

90)

**Tensile strength:** 2.5MPa (≥2.0)

**Elongation at break:** 99% (≥90)

Flame retardant: Class I, Qualified

**Ball rebound rate:** 93% (≥90%)

**High temperature test (100°C, 24h) :** no melting and no obvious color difference after

the test

Low temperature test (-40°C, 24h): no cracking or obvious color difference after the test

**Sliding friction coefficient:**  $1.2 (0.4 \sim 1.5)$ 

Aging resistance (168h)

- Appearance quality after aging: uniform color after aging, no obvious color difference, no cracks, stratification and other defects
- Tensile strength after aging: 2.2MPa
  (≥2.0)
- Elongation at break after aging: 91%
  (≥80)



### No: GT901299

Sample name: PVC indoor sports flooring

**Inspected unit:** Xiongxian LAIKEMAN Plastic

Floor Co., LTD

Manufacturer: Xiongxian LAIKEMAN Plastic

Floor Co., LTD

Trademark: LAIKEMAN

Sample description: No abnormality was

found in the sample

**Production date/Batch number: 2019.4.12** 

**Inspection Date:** 2019/4/17 to 2019/4/29

**Inspection basis:** GB 18586-2001 "Limits of Harmful Substances in PVC Building Materials

Floor of Interior Decoration Materials"

**Inspection items:** vinyl chloride monomer limit, soluble heavy metal limit, volatile substance limit

Inspection conclusion: The sample was tested according to GB 18586-2001 "Limit of Harmful Substances in PVC Building Materials Floor of Interior Decoration Materials", and the inspected items were qualified.

Date of issue: 29 April 2019

## No: GT901299 Item of Inspection

**Limit of vinyl chloride monomer:** qualified, not detected (detection limit 0.1mg/kg) Qualified, (≤5)

#### Soluble heavy metal Limit

- Soluble lead content: qualified, 0.1mg/m²
  (≤20)
- Soluble cadmium content: qualified,
  0.1mg/m² (≤20)



国家体育用品质量监督检验中心 检验检测报告 共3页第1页 II No 规格型号 样品名称 PVC室外运动地板 商 莱珂曼 委托单位 維县莱珂曼塑胶地板有限公司 样品等级 委托单位 地址 河北省保定市雄县雄州镇地热局南侧 送样人 李文杉 維县莱珂曼塑胶地板有限公司 检验类别 委托检验 受检单位 生产单位 維县莱珂曼塑胶地板有限公司 样品数量 4 块 样品描述 样品未见异常 生产日期/批号 2019. 4. 1 2019/4/17 至 2019/4/29 到样日期 2019/4/17 检验日期 检验依据 GB/T14833-2011《合成材料跑道面层》 阻燃、苯、甲苯和二甲苯总和、游离甲苯二异氰酸酯、重金属、拉伸强度、拉斯伸长 检验项目 检验结论 该样品按GB/T14833-2011《合成材料跑道面层》标准检验, 所检项目合格 签发日期: 2019年4月29日 备 注 检验:张京京 批准: 海蚌 审核: 44-7

• Volatile substance limit: qualified, 13g/m² (≤40)

## No:GT1901300

Sample name: PVC outdoor sports flooring

**Inspected unit:** Xiongxian LAIKEMAN Plastic

Floor Co., LTD

Manufacturer: Xiongxian LAIKEMAN Plastic

Floor Co., LTD

Trademark: LAIKEMAN

Sample description: No abnormality was

found in the sample

**Production date/Batch number: 2019.4.1** 

**Inspection Date:** 2019/4/17 to 2019/4/29

**Inspection basis:** GB/T14833-2011 "Synthetic

Material Runway Surface"

**Test items:** flame retardant, benzene, toluene and xylene total, free toluene diisocyanate, heavy metal, tensile strength, elongation at break

Inspection conclusion: The sample was tested according to GB/T14833-2011 "Synthetic Material Runway Surface" standard, and the inspected items were qualified.

Date of issue: 29 April 2019

序号		检验项目	单位	技术要求	检验结果	单项判定
1	苯		g/kg	≤0.05	未检出(检出限 0.02g/kg)	合格
2	甲苯和二甲苯总和		g/kg	≤0.05	未检出(检出限 0.02g/kg)	合格
3	游离甲苯二异氰酸酯		g/kg	≤0.2	未检出(检出限 0.1g/kg)	合格
	可溶性铅		≤90	未检出 (检出限 1.0mg/kg)	合格	
	4 重金属	可溶性镉		≤10	未检出(检出限 0.3mg/kg)	合格
4		可溶性铬	mg/kg	≤10	未检出(检出限 0.4mg/kg)	合格
		可溶性汞		≤2	未检出(检出限 0.003mg/kg)	合格
5	阻燃		级	I	I	合格
6	拉伸强度		МРа	≥0.5	3. 3	合格
7	拉断伸长率		%	≥40	176	合格
	备注: "	√"表示符合技术要求	,"×"表示不	、符合技术要求。"——"表示	示未检或不作判定。以下	空白。

# No:GT1901300 Item of Inspection

**Benzene:** qualified, not detected (detection limit: 0.02g/kg) (≤0.05)

**Toluene and xylene total:** qualified, not detected (detection limit: 0.02g/kg) (≤0.05)

Free toluene diisocyanate: qualified, not detected (detection limit 0.1g/kg) ( $\leq 0.2$ )

#### **Heavy metal**

- **Soluble lead:** qualified, not detected (detection limit 1.0mg/kg) (≤90)
- **Soluble cadmium:** qualified, not detected (detection limit 0.3mg/kg) (≤10)
- **Soluble chromium:** qualified, not detected (detection limit 0.4mg/kg) (≤10)
- **Soluble mercury:** qualified, not detected (detection limit 0.003mg/kg) (≤2)

Flame retardant: Class I

**Tensile strength:** Qualified, 3.3MPa (≥0.5)

**Elongation:** Qualified, 176% (≥40)